HESKINS
ANTI-SLIP SOLUTIONS
mail@heskins.com www.heskins.com 26/06/2021

Heskins H3415 coarse resilient data sheet, new version

Subject	Result
Composition	PVC upper and PET base
Type of adhesive	Solvent acrylic
Overall thickness (mm)	1.3mm
Tackloop (kg/25.4mm)	6.23
Cohesion (minutes/25°C)	2812↑
Applied Weight	1280 g/m²
Adhesion to steel (kg/25.4mm)	5.714
Temperature range	-10°C ~ 80°C
Maximum roll size	1371mmx100m
Life (months)	12 to 24

LRV Test Results

Material/Colour	Av. LRV	Range
H3415N (Black)	0.5	1
H3415S (Grey)	5.75	1
H3415W (White)	78.5	1
H3415T (Transparent)	47.5	12
H3415Y (Yellow)	44.5	1

Coefficient of friction data

	Dry surface test result	Wet surface test result
H3415 Coarse resilient	95 TRL	60 TRL

	Coefficient of Friction Category	Test
H3415 Coarse Resilient	R10	DIN51130

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins Ltd 1997-2021

ISO 9001 CERTIFIED British Assessment Bureau
ISO 14001 CERTIFIED British Assessment Bureau